



Metl-Clad Metal Primer

449 Gray Metal Primer

Product Data Sheet

DESCRIPTION and USES

This product is an excellent rust preventive primer for iron and steel surfaces. It contains Barium Metaborate, a non-toxic, rust inhibitive pigment. It also contains Mica, a pigment that forms a protective layer that bridges micro pores in the paint film, preventing moisture and air from reaching the metal surface. These pigments are ground into Alkyd Resins and Linseed Oil which penetrate rusted surfaces to stop and prevent corrosion. This product is effective on all ferrous metal surfaces, interior or exterior.

SURFACE PREPARATION

Best results are obtained with the best surface preparation. Commercial grade sandblasting to remove rust and mill scale is best. Power tool or hand removal of rust and scale is less effective but better than no preparation. Surface must also be dry and free of oil and dirt.

APPLICATION

Apply with brush, roller or spray making sure all areas, especially edges, are well coated. Avoid application, if possible, when temperatures are above 90°F or below 50°F or when relative humidity is above 85%. Use as supplied. Do not thin.

SAFETY INFORMATION

For complete safety information, refer to the SAFETY DATA SHEET for this product.

COLORS

Light Gray (May be tinted with up to 4 oz. Universal Colorant per gallon).

The suggestions for use and technical data here given are accurate to the best of our knowledge and are offered in good faith. Because the conditions and use of our products are beyond our control, our liability, if any, is limited to the replacement of defective material only. RepcoLite Paints, Inc. DISCLAIMS ALL OTHER WARRANTIES relating to our products and DISCLAIMS ALL WARRANTIES RELATING TO THEIR APPLICATION, expressed or implied, INCLUDING but not limited to warranties of merchantability and fitness for a particular purpose. TECHNICAL DATA IS SUBJECT TO CHANGE WITHOUT NOTICE.

TECHNICAL DATA

Vehicle Type:	Alkyd Resins and Linseed Oil
Volume Solids:	48%
Coverage:	400 – 450 SF/Gallon
Dry Time:	
<i>Touch:</i>	6 – 8 Hours
<i>Recoat:</i>	Overnight
VOC:	Less than 400 g/l
Clean Up:	Paint Thinner (Mineral Spirits)

PRODUCT CODE INFORMATION

44917 Metl-Clad 449 Metal Primer—Lt. Gray

RepcoLite Paints, Inc.

473 W. 17th St.

Holland, MI 49423

(616) 396-1275

www.repcolite.com