

DESCRIPTION and USES

This exterior wood stain provides a rich, velvety finish on new or previously stained wood. It combines durable pigments and 100% acrylic resin for maximum durability and resistance to fading. While this stain hides the color and grain of the wood, it allows the texture of the wood to remain. It's excellent covering ability makes it ideal for use when color changes are made. This stain has very good weather resistance, color retention and ease of application. It is ideal for use in restraining previously stained surfaces in good condition. Do not use on horizontal surfaces such as decks and furniture.

PREPARATION

Surface Preparation: All cutting, gluing, and sanding of the wood should be done before coating. Surfaces to be stained must clean, dry, and free of contaminants such as dirt, oil or wax. If mildew is present, clean the surface with a 50% solution of household bleach and water. New pressure-treated wood should be allowed to dry for at least 30 days. New cedar should have the mill glaze removed through sanding or an oxalic acid-based cleaning/brightener product. Discoloration can be removed and the wood restored to its natural color by using a wood brightener. Rinse well after these treatments. Wear protective gloves, clothing, and goggles when working with bleach or wood brightener. Power washing to remove old or peeling stain is recommended. Allow 2 days for wood to dry after rain, rinsing, or power washing before staining.

APPLICATION

Stir thoroughly before and occasionally during use. Stains are best applied with a natural bristle brush, paint pad, or special stain applicator. Rolling and spraying may also be used, but the stain should be worked into the pores of the wood with a brush immediately after application with these methods. Maintain a wet edge by staining only a few boards at a time. Use as supplied. Do not thin.

SAFETY INFORMATION

For complete safety information, refer to the SAFETY DATA SHEET for this product.

The suggestions for use and technical data here given are accurate to the best of our knowledge and are offered in good faith. Because the conditions and use of our products are beyond our control, our liability, if any, is limited to the replacement of defective material only. RepcoLite Paints, Inc. DISCLAIMS ALL OTHER WARRANTIES relating to our products and DISCLAIMS ALL WARRANTIES RELATING TO THEIR APPLICATION, expressed or implied, INCLUDING but not limited to warranties of merchantability and fitness for a particular purpose. TECHNICAL DATA IS SUBJECT TO CHANGE WITHOUT NOTICE.

TECHNICAL DATA

Finish:	Flat
Vehicle Type:	100% Acrylic
Volume Solids:	31-35%
Coverage:	150 – 300 SF/Gallon (depending on surface porosity).
Dry Time:	
<i>Touch:</i>	30 Minutes
<i>Recoat:</i>	4 Hours
VOC:	Less than 75 g/l
Clean Up:	Water

COLORS

Available in a virtually limitless color range. Use RepcoLite's Waterborne Zero VOC Color System

PRODUCT CODE INFORMATION

46810	Woodmaster Latex Solid Color Stain – 411 Base
46802	Woodmaster Latex Solid Color Stain – 412 Base
46803	Woodmaster Latex Solid Color Stain – 413 Base
46806	Woodmaster Latex Solid Color Stain – 416 Base

RepcoLite Paints, Inc.

473 W. 17th St.

Holland, MI 49423

(616) 396-1275

www.repcolite.com