

DESCRIPTION AND USES

Mira-Poly Sanding Sealer is used after the staining process, before the final finish. The purpose of **Mira-Poly Sanding Sealer** is to provide a high-building, fast-drying, and easy-sanding intermediate clear coat on interior vertical surfaces. It is not recommended for floors or other surfaces subject to heavy wear. **Mira-Poly Sanding Sealer** does not contain zinc stearates so it may be used under urethane varnishes.

SPECIFICATIONS

SURFACE PREPARATION: Sand bare wood with 120 grit sandpaper.

APPLICATION: Apply to bare or previously stained wood with a natural bristle brush, pad applicator, or spray. Allow a minimum of 45 minutes of dry time between coats. Always sand between coats using 180 grit sandpaper. Allow at least two hours of dry time before final coating with **750 Series Mira-Poly Polyurethane Varnish**. Do not use lacquer or shellac as a finish coat.

CLEAN UP: Use paint thinner (Mineral Spirits).

PRECAUTIONS

NOTICE: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuses by deliberately concentrating and inhaling the contents may be harmful or fatal.

For complete safety information, refer to the MATERIAL SAFETY DATA SHEET for this product.

COMPANION PRODUCTS

- 750 Series Products
- 800 Series Stains, Glazes and Toners
- 400 Series Stains and Fillers

PRODUCT CODES

750S - Clear Sanding Sealer

TECHNICAL DATA

VEHICLE TYPE: Alkyd Resin

VOLUME SOLIDS: 30%

WEIGHT SOLIDS: 37%

DENSITY: 7.1 lbs/gal

ACTUAL VOC: 4.38 lbs/gal

REGULATORY VOC: 526 g/L

CLEAN UP SOLVENT: Mineral Spirits

COVERAGE: 300 - 500 square feet at 1 mil dry film thickness.

DRY TIME: 45 Minutes (see application info.)

SHELF LIFE: 1 year shelf life when properly stored.

For complete safety information, refer to the SAFETY DATA SHEET for this product.

RepcoLite
Quality Paint Since 1946

RepcoLite Paints, Inc.
473 W. 17th St.
Holland, MI 49423
(616) 396-1275
www.mirafinishes.com